

PLASTOIL

Chlorinated Paraffin

Specification	Test Method	1040	1045	152
Color, APAH (max)	ASTM D1209-69	200	120	120
Chlorine Content by wt %	ASTM E442	40~42	44~46	50~52
Specific Gravity, 25°C	ASTM D287	1.13~1.18	1.14~1.19	1.23~1.27
Viscosity, 25°C (Poise) (max)	JISK2283	20~35	2~3	11~16
Thermal Stability, % HCL (4hrs 175°C)	JQD Method	0.2	0.2	0.2
Acid Value, (mg KOH/g) (max)	JISK2501	0.15	0.15	0.15

Packing: i) 1040 & 1045 – 230kg/renew iron drum, 80 drums & 18.4MT in 20'FCL
 ii) 152 – 250kg/renew iron drum, 76 drums & 19MT in 20'FCL

Origin: Taiwan