

## Egyptian European Company

Factory: Alexandria Public Free Zone Area, Alexandria - Egypt

Head Office: 8A Taha Hussein Rd. New Nozha – Cairo, Egypt

Tel/Fax: +203 4542128 - Mobile:+201 222 111 903

E-mail: [eecalex@pccplastic.net](mailto:eecalex@pccplastic.net) Website : [www.pccplastic.com](http://www.pccplastic.com)

**PUBLIC FREE ZONE**

### Polyethylene Powder for Rotational Molding

**Egyeuroptene MD 3704 U\*** is a Medium Density Polyethylene powder, designed for Rotational molded items:

**Road barriers, Containers, Tanks, Garbage cans, Flower pots, Feed carts and Toys.**

Property	Test Method	Unit	Value
Melt Flow Rate (190/ 2.16 Kg)	ISO 1133	g/10min	3.7
Density	ISO 1872/1	g/cm <sup>3</sup>	0.937
Tensile Strength at Yield	ISO 527/1	MPa	17.3
Elongation at Break	ISO 527/1	%	990
Flexural Modulus	ISO 178 1975	MPa	900
ESCR, F50, 23°C	ASTM 1693	Hrs	55
Charpy Impact Resistance	ISO 179	KJ / M <sup>2</sup>	31
Mean Particle Size	ASTM D1921-89	Micron	500
Bulk Density	ASTM D 1895	g/cm <sup>3</sup>	0.37
Fluidity	ASTM D 1895	Seconds	26

\* U = UV Stabilized



URS CERTIFICATE NO.



URS CERTIFICATE NO.



URS CERTIFICATE NO.



043

The data and information given within this datasheet are to the best of our knowledge based upon experiments and tests which EEC believes to be reliable and only indicated as a typical properties. This datasheet does not constitute any specification limits. Unless specifically indicated, all above values are related to the base resin.